

Flexitallic

n novusTM
a Flexitallic brand


WILLIAM JOHNSTON
& COMPANY LIMITED

Data / Specification Sheet • Novus 34

Novus 34 is a superior performance universal compressed sheet material based on a blend of aramid/ inorganic fibres and special additives, with high quality nitrile rubber binder system.



Service

Novus 34, a superior performance material with excellent mechanical properties, it is suitable for many applications including oils, solvents, high pressure steam and gases including oxygen.

Approvals / Compliance

WRAS Potable Water: Registration No. 1406501

BAM (Oxygen service) up to 90°C and 160 bar

Complies with BS Specification 7531 Grade X

TA-LUFT (in accordance with VDI Guideline 2440)

GL Approval cert 37702 – 12HH

Availability

Thickness range:
0.25mm to 6.0mm

Standard sheet sizes:

2.0m x 2.0m

2.0m x 1.5m

2.0m x 1.0m

1.5m x 1.5m

1.5m x 1.0m

Standard roll sizes:

Up to a maximum size of 6.0m x 2.0m

Available with fine mesh mild steel reinforcement: Novus 34 Metallic or gauze mild steel wire reinforcement: Novus 34 GWI.


It can be supplied with anti-stick coating and graphite coating.

Typical Physical Properties

Thickness		1.5mm
Density		1.75g/cc
Tensile Strength	ASTM F152	9-11 MPa
Compression	ASTM F36	9%
Recovery	ASTM F36	55% min
Residual Stress	BS 7531 (300°C) DIN 52913	26MPa 32MPa
Gas Leakage	BS 7531	<1.0cc/min
ASTM Oil 1	Thickness increase	1.0%
IRM 903 Oil	Thickness increase	2.5%
ASTM Fuel B	Thickness increase	3.0%

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only, and without liability on the part of the company.

Novus 34 Pressure/Temperature Limits



- 1 Suitable subject to chemical compatibility.
- 2 Suitable in some cases but check your application requirements with Flexitallic.
- 3 Contact the Technical Team for applications with higher temperatures and pressures. Applicable to 2.0mm and below.

The operating temperature of non-asbestos sheet material is related to the thickness of materials selected. Thinner materials give better temperature and pressure properties.

 **WILLIAM JOHNSTON**
& COMPANY LIMITED

Disclaimer
Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.

HEAD OFFICE: 9 Spiersbridge Terrace, Thornliebank Ind. Estate, Glasgow G46 8JH

Tel: +44 (0) 141 620 1666 Fax: +44 (0)141 620 1888 Email: sales@williamjohnston.co.uk www.williamjohnston.co.uk